



9079 Tyler Blvd., Mentor, OH 44060

Product name: xm18o 100 PU

FEATURES

- Good initial adhesion
- Breathable
- Gentle adhesion on skin
- Good for ostomy ring sealant
- Good saline absorbance

COMPOSITION

Backing: 1.0 mil polyurethane film

Adhesive: 100 mil hydrocolloid adhesive

Release liner: 3.4 mil 60# SCK paper release liner

TYPICAL PROPERTIES

Test	Method	Typical Average Value
Probe Tack	Modified ASTM D2979	500-700 grams
Static Shear	Modified ASTM D3654A	50-80 minutes
Saline Absorption	Xennovate Internal Method	90-110%
Liner Release	ASTM D 5357	50-80 grams

Test method details are available upon request. Values listed here are typical average values and should not be interpreted as a specification.

ROLL DESCRIPTION

Standard rolls are 9.25" wide, 100 feet long, 6" core.

RECOMMEDED STORAGE

Store in sealed, poly bags at normal room temperature (65 to 75 ° F) and dry environment. Avoid storage in temperatures above 85°F. Keep rolls in the end-cap suspended packaging supplied by Xennovate Medical[®].

Shelf Life

To obtain best performance, use this product within 12 months from date of manufacture.